Solid-State NMR as A Powerful Tool to Characterize Polysaccharide-Based Systems

CELL 57

ACS Spring 2020 National Meeting & Expo

Division of Cellulose and Renewable Materials (CELL)

Advances in Methodology for Structural Characterization of Cellulosic & other Polysaccharide-Based Systems

Francesco D'Acierno

22/03/2020

🎤 I'm spinning in the field... 🎤

- **NMR Spectroscopy** = Nuclear Magnetic Resonance Spectroscopy.
- **Nuclear** → It exploits the nuclear **spins'** movement of every isotope.
- **Magnetic** → A strong magnetic **field** is required to align all the nuclear spins.
- **Resonance** → A weak magnetic field at a resonant frequency is used to **perturb** the spins of nuclei.
- **Spectroscopy** → The characteristic frequency of those nuclei is **converted** into a spectrum.

Solutions vs Solids

- **Solution-state NMR (NMR)**

Brownian motion averages anisotropic interactions to *zero*, and the number of peaks depends on the *molecular* symmetry.

- **Solid-state NMR (ssNMR)**

Anisotropic interactions in less mobile nuclei are *relevant*, and the number of peaks depends on the *crystallographic* symmetry.

Solution State NMR vs Solid State MAS NMR

University of Ottawa NMR Facility Blog (accessed on March 9th, 2020).

MRI Questions (accessed on March 9th, 2020).

Solid-state NMR of Polysaccharides

- Polysaccharides are **naturally-occurring polymers** made of simple **sugars** with *storage* (e.g., starch) or *structural* functions (e.g., cellulose and chitin).
- Solid-state NMR is a powerful technique to **characterize** them because:
 - They can form complex **supramolecular** structures;
 - They have a very large fraction of **amorphous** regions;
 - They are generally **porous**;
 - Their **surface-to-volume** ratio is high when extracted at the nanoscale.

	Cellulose	Starch		Glycogen
		Amylose	Amylopectin	
Source	Plant	Plant	Plant	Animal
Subunit	β -glucose	α -glucose	α -glucose	α -glucose
Bonds	1-4	1-4	1-4 and 1-6	1-4 and 1-6
Branches	No	No	Yes (~per 20 subunits)	Yes (~per 10 subunits)
Diagram				
Shape				

Healing Herbs (accessed on March 13th, 2020).

Structural Characterization

Cellulose

Delepierre, et al. (in preparation).

- Cellulose has the same **molecular** structures in **allomorphs** BUT distinct **supramolecular** structure.
- There are **differences** in all ^{13}C sites.

D'Acerno, et al. (in preparation) Djahedi, et al. *Carbohydr. Polym.* **2015** (modified).

Structural Characterization

- **Thermal degradation** of cellulose materials induces dramatic structural **conversion**.
- **Distribution** of site intensities enables identification of decomposition **mechanism**.

D'Acerno, et al. (in preparation).

Delepierre, et al. (in preparation).

D'Acerno, et al. (in preparation).

Surface Molecular Environment

^1H - ^{13}C CP/MAS NMR

Aalbers, Boott, et al.
Biomocromolecules 2019.

^{19}F - ^{13}C CP/MAS NMR

^{19}F MAS NMR

Aalbers, Boott, et al.
Biomocromolecules 2019.

^1H - ^{13}C CP/MAS NMR

Delepierre, et al. (in preparation).

^{23}Na MAS NMR

Vanderfleet, D'Acierno, et al. (in preparation).

^1H - ^{13}C CP/MAS NMR

Liu, et al. (in preparation).

Nyamayaro, Keyvani, et al. *ACS Appl. Mater. Interfaces* (submitted).

Surface Molecular Environment

^1H - ^{13}C CP/MAS NMR

^{19}F - ^{13}C CP/MAS NMR

^{19}F MAS NMR

Aalbers, Boott, et al.
Biomacromolecules 2019.

^{23}Na MAS NMR

Vanderfleet, D'Acierno, et al. (in preparation).

- Cellulose nanocrystals can be **grafted** at the surface with **aliphatic** and **fluoroalkyl** chains $\rightarrow$ ^{19}F NMR can help study.
- Creation of hydrophobic oil **absorbents**.

Aalbers, Boott, et al. *Biomacromolecules* 2019.

Nyamayaro, Keyvani, et al. *ACS Appl. Mater. Interfaces* (submitted).

Aalbers, Boott, et al.
Biomacromolecules 2019.

Surface Molecular Environment

- Cellulose nanocrystals can also be **grafted** at the reducing **ends**.
- End-grafting can be used to create **thermally switchable** liquid crystals.

^1H - ^{13}C CP/MAS NMR

Aalbers, Boott, et al.
Biomacromolecules 2019.

^{23}Na MAS NMR

Vanderfleet, D'Acierno, et al. (in preparation).

^1H - ^{13}C CP/MAS NMR

Delepierre, et al. (in preparation).

^1H - ^{13}C CP/MAS NMR

Liu, et al. (in preparation). *p-IPAM-g-CNCs*

Nyamayar, Risteen, et al. *Small* 2018. *Water. Interfaces* (submitted).

Aalbers, Boott, et al.
Biomacromolecules 2019.

Surface Molecular Environment

- Acid cellulose nanocrystals can be pH-neutralized by exchanging proton with sodium ions at the surface (CNC-Na).
- ^{23}Na NMR provides insights of the environment around the sodium ion both at room temperature and after pyrolysis.

^{23}Na MAS NMR

Vanderfleet, D'Acierno, et al. (in preparation).

Nyama, Vanderfleet, D'Acierno, et al. (in preparation).

Surface Molecular Environment

- The surface of cellulose nanocrystals can be **functionalized** with cationic or anionic groups to transform CNCs in **ionic conductors**.
- First step towards the development of **CNC-based** lightweight, flexible, biocompatible and biodegradable **electronic devices**.

Liu, et al. (in preparation).

Nyamayaro, Keyvani, et al. *ACS Appl. Mater. Interfaces* (submitted).

Aalbers, Boott, et al.
Biomacromolecules 2019.

Vanderfleet, D'Acierno, et al. (in preparation).

Surface Molecular Environment

- Other **polysaccharide nanomaterials**, such as **chitin nanocrystals**, can be easily grafted to **hydrophobic** chains with high degree of substitution.
- Functionalized chitin nanocrystals have high potential in the field of **dental** materials, as fillers of antibacterial and biodegradable resin **adhesives**.

^1H - ^{13}C CP/MAS NMR

Liu, et al. (in preparation).

Your Dentistry Guide (accessed on March 20th, 2020):s (submitted).

Aalbers, Boott, et al.
Biomacromolecules 2019.

Vanderfleet, D'Acierno, et al. (in preparation).

Polysaccharide-Templated Inorganic Materials

CONTROLLED COLOR RANGE
COMPLETE RGB GAMMA
GAMUT TOLERANCE

^{27}Al MAS NMR

Nguyen, et al. *Chem. Mater.* 2018.

^{27}Al 3Q MQMAS NMR

Nguyen, et al. *Chem. Mater.* 2018.

^{11}B MAS NMR

Nguyen, et al. (in preparation).

^{29}Si spin-echo MAS NMR

Terpstra, et al. *Adv. Opt. Mater.* 2018.

Polysaccharide-Templated Inorganic Materials

Nguyen, et al. *Chem. Mater.* 2018.

Nguyen, et al. *Chem. Mater.* 2018.

- **Chitosan** can easily form **complexes** with aluminum ions from nitrate salts, and when calcined **porous alumina** aerogels can be obtained.
- **^{27}Al NMR** enables the identification of the **structure** as a function of **calcination time**.
- The **discrimination** of all sites is achieved through **MQMAS**.

Terpstra, et al. *Adv. Opt. Mater.* 2018.

Polysaccharide-Templated Inorganic Materials

- **Cellulose nanocrystals** can be combined with **boric acid** and calcined in a nitrogen-enriched atmosphere to fabricate cheap, biotemplated **carbon-doped boron nitride**.
- Carbon-doped boron nitride is a powerful **superconductor** and conventional fabrication methods are **expensive**.

Nguyen, et al. (in preparation).

Terpstra, et al. *Adv. Mater.* 2019. Wikipedia (accessed on March 20th, 2020).

Nguyen, et al. *Chem. Mater.* 2018.

Nguyen, et al. *Chem. Mater.* 2018.

Polysaccharide-Templated Inorganic Materials

- Templating cellulose nanocrystals with **organosilica** is possible to create mesoporous, iridescent, and **chiral nematic** materials.
- Alkylene **spacers** of variable length are used to **tune** the color and the porosity of the templated materials.

Terpstra, et al. *Adv. Opt. Mater.* 2018.

Nguyen, et al. *Chem. Mater.* 2018.

Terpstra, et al. *Adv. Opt. Mater.* 2018.

Nguyen, et al. (in preparation).

Terpstra, et al. *Adv. Opt. Mater.* 2018.

Magnetic Field Exploitation

CONTROLLED COLOR RANGE
COMPLETE RGB GAMMA
GAMMA TOLERANCE

Cranston, *Gray Sci. Technol. Adv. Mater.* 2006.

Cao, Wang, et al. *Adv. Mater.* 2020.

— Pitfalls —

- **Complex** molecules at a **very low concentration** are difficult to detect.
- Some components of the **probe** are made in **cobalt, copper and titanium**, so the noise in ^{59}Co , ^{63}Cu and ^{49}Ti can compromise the measurements.

Zhang, Soto, et al. *Angew. Chem. Int. Ed.* 2020

Conclusions and Future Directions

- **Structural** ssNMR characterization enables to distinguish different **supramolecular** structures and **quantify** functional groups.
- The **surface** of polysaccharide (nano)materials can be **investigated** in details, also exploiting other isotopes (e.g., ^{23}Na and ^{19}F).
- Polysaccharides can be used to **template inorganic** functional materials and ssNMR can study their nature tuning at resonant frequencies of **quadrupolar** isotope spins.
- The strong magnetic **field** used for ssNMR can be exploited to **orient** domains of polysaccharide suspensions and hydrogels.
- Issues are experienced when the fraction of one of the species is **below the detection limit**, or when isotopes included in the **probe structure** are investigated.
- **Many other** polysaccharides can be analyzed, both in macro- and nanoscopic form, as well as study the **ionic mobility** of new kind of electronic devices.

Contact Info

CONTROLLED COLOR RANGE
COMPLETE RGB GAMMA
GAMMA TOLERANCE

- **Name:** Francesco D'Acierno
- **Position:** Ph.D. Candidate at UBC Chemistry
- **Email:** fradaci@chem.ubc.ca
- **Google Scholar:**
https://scholar.google.ca/citations?user=T_jaxpYAAAAJ&hl=en
- **Twitter:**
<https://twitter.com/fdacierno>

Thank you.