Removal of organic contaminants from water by using the polypropylene-based monoliths

By

Nadeem Baig^{*1,2}, Tawfik A. Saleh¹

¹Chemistry Department, King Fahd University of Petroleum and Minerals, Dhahran 31261, Saudi Arabia.

²Center for Research Excellence in Desalination & Water Treatment, King Fahd University of Petroleum and Minerals, Dhahran 31261, Saudi Arabia

Email: nadeembaig@kfupm.edu.sa; nadeembaig38@gmail.com

Introduction

- Organic contaminants in water are the major contributor in water pollution
- The oil related organic contaminants in water are being added by food industries, textile, petrochemical and periodical oil spills incidents.¹
- The organic contaminants are continuously increasing due to rapid industrialization, urbanization and high energy demands from conventional sources
- To get rid of oil and oil related organic contaminants from water various conventional methods are used such as skimmers, solidifiers, bioremediation, and dispersants.
- Some of these methods are suffering from high cost, poor separation efficiency and can become a source of addition of secondary pollutants.²
- There is a need to develop new material that display specificity towards the organic pollutants in water
- The hydrophobic and oleophilic porous surfaces can be proved impressive for the selective separation of the oil-related contaminants from the water.

Synthesis of Magnetic Monolith of PP³

Synthesis of iron oxide magnetic nanoparticles

- co-precipitation method was used
- The solutions of $\text{FeCl}_2 \cdot 4\text{H}_2\text{O}$ and $\text{FeCl}_3 \cdot 6\text{H}_2\text{O}$ were mixed
- Ammonia added until pH reach about to 10
- Reflux at 90 C for 6 hours
- Permanent magnet was used to remove magnetic nanoparticles from the obtained solid

Development of polypropylene magnetic monolith

- Polypropylene fibers were dipped into iron oxide magnetic solution
- Polypropylene dried and dipped again until polypropylene fibers attracted towards magnet.
- Styrene polymerized to polystyrene on the magnetic nanoparticles decorated PP

Results & Discussion³

Morphological characterization

EDX and FTIR Spectra

Magnetic behavior and water CA

Absorption capacity

Separation of organic contaminants from water

Conclusion³

- ❖ Introduction of magnetic nanomaterial improved the surface area of the monolith to $221 \text{ m}^2/\text{g}$.
- ❖ PS coated Magnetic PP was found magnetically active
- ❖ Developed PS coated Magnetic PP has exhibited good hydrophobicity with water contact angle of 146.54° .
- ❖ PS coated Magnetic PP can be used for the spot removal of the organic contaminants from the water
- ❖ The absorption capacity of PS coated Magnetic PP was found in the range of 1023–1517%
- ❖ PS coated Magnetic PP can be used for dynamic separation of non-polar organic contaminants
- ❖ During separation of the heptane and water the flux of $13365 \text{ Lm}^{-2}\text{h}^{-1}$ was observed
- ❖ It can be used multiple time for the separation of the non-polar organic contaminants from water
- ❖ Synthesis process is simple and cost-effective and can be used for large scale production

References

1. Wang, X.; Yu, J.; Sun, G.; Ding, B. Today 2016, 19 (7), 403–414. <https://doi.org/10.1016/j.mattod.2015.11.010>
2. Wang, N.; Wang, Y.; Shang, B.; Wen, P.; Peng, B.; Deng, Z. J. Colloid Interface Sci. 2018, 531, 300–310. <https://doi.org/10.1016/j.jcis.2018.07.056>
3. Baig, N.; Saleh, T. A. Compos. Part B Eng. 2019, 173, 106805. <https://doi.org/10.1016/j.compositesb.2019.05.016>

Acknowledgement: Authors gratefully acknowledge the support provided by the “King Fahd University of Petroleum and Minerals, Dhahran, Saudi Arabia”.