THE CLINICAL, BIOCHEMICAL AND BIOPHYSICAL SIGNATURE OF BRITTLE NAILS

ENEA CASSE R; LETAILLANDIER C ; CAVUSLOGUN N;
FIAT F; FONTENEAU S; FORMANEK F
FOUCHER A; PELE D ; POTTER A;
VICIC S; LEROY F; CASTIEL-HIGOUNENC I;
GUENICHE A

L'Oréal Research & Innovation, France

INTRODUCTION

- Providing a reliable scientific knowledge on nail health and appearance (healthy/normal vs brittle)
- Proposing a pool of available techniques to access nails characteristics.
- Building a Structural – Morphological – Functional approach to look at nails (or other (bio)materials)

RESULTS

Morphological changes

Transmission Electron Microscopy (TEM)

TEM: The intercellular spaces are more pronounced in brittle nails, as well as the presence of smaller cornodesmosomes

OCT (Optical Coherence Tomography)

The density of brittle nails is decreasing, comparing to the healthy ones as seen with OCT. Results correlate well with TEM (where cornodesmosomes cohesion is affected) and explain the mechanical weakness of brittle nails (as measured with AFM).

AFM (mechanical strength and elasticity)

Elasticity healthy vs brittle

Topography (AFM) et morphology (TEM) on the same sample

A strong decrease of the E for brittle nails. These results are correlated with the μ -fluorescence (less Sulphur/ Calcium), Raman, TEM as well as density profiles by μ -tomography, and OCT

LIPIDS ANALYSIS AND RAMAN SPECTRA OF LAMELLAR LIPIDS

AA quantification in Nails, by enzymatic reaction

Using complementary techniques such as GC/MS and LC/MS lead us to find that there is a strong decrease in ceramides and neutral lipids (sterols, amides) and increase in free fatty acids for brittle nails.

Importance of the S-S bonds, S-rich AminoAcids AND PROTEOMIC

AA detection: **Less Cystein** detected in brittle nails.

Raman: **Two times less stable S-S bonds** in brittle nails, which correlates well with mechanical results and μ -X Ray (density, porosity).

Using dedicated ELISA with specific proteins, it was found that **Annexin A2, Galectin 3, Serpin A12 and GAPDH** are dysregulate in brittle nails.

CLINICAL STUDY

Population description from the clinical study:

Parameter scoring by esthetician	Brittle nails (44 women volunteers)		Healthy nails (38 women volunteers)		P<H
	Mean	SD	Mean	SD	
Onychoschizia - Fractionnement lamellaire	0.274	0.064	0.155	0.069	0.2069
Onychoschizia - Fractionnement transversal	0.700	0.076	0.239	0.082	<0.0001
Onychomexis-Sites	1.387	0.085	0.777	0.092	<0.0001
Onychomexis - Fractionnement longitudinal	0.061	0.062	0.001	0.024	<0.0001

X-Ray Nail structural organisation

A crystalline organization for the keratin molecules was observed in the SAXS and WAXS spectra, for all 3 specific zones of the nails (ventral, intermediate, dorsal), which is related to a well, healthy organized molecular structure, meaning that the onychoschizia or onychorrhexis of nails doesn't affect the inner organization of nails.

μ -tomography (porosity and density)

Total: 10 times more pores for brittle nails. Mean: $124 \pm 50 \mu\text{m}^3$ brittle vs $37 \pm 29 \mu\text{m}^3$ healthy (3 times bigger)

The density of brittle nails is lower compared to the healthy ones, and especially for the dorsal zones (the external one), this result is in correlation with TEM, OCT and AFM.

μ -fluorescence (elements detection)

Strong decrease in the Sulphur and Calcium distribution in the brittle nails or brittle nails.

CONCLUSION

A brittle nail's signature:

- Greater intercellular spaces between cells, with smaller desmosomes, which are highly detrimental to nail strength
- A strong decrease in density and great changes in porosity;
- Twice less stable S-S bonds, less Cystein, as well as more energetically instable form of proteins
- Less neutral lipids (sterols, amides) and acylceramides but more free fatty acids
- A strong deregulation of several biomarkers, implicated in barrier function and desquamation
- A decrease in Sulfur and Ca²⁺ gradient (calcium plays a key role in the intercellular cohesion as well as in the desquamation process);

Regarding Nail Barrier function, a strong deregulation of several biomarkers was found in brittle nails. This process is altered in brittle nails as compared to healthy nails, and this damaged process is highly detrimental for nail strength.

All the results are essential and open the way to new mechanistic approaches for designing innovative nail care products.