CHEMICALLY MODIFIED SURFACES FOR THE SEPARATION OF NON-POLAR ORGANIC CONTAMINANTS FROM THE WATER

By

Nadeem Baig^{*1,2}, Tawfik A. Saleh¹

¹Chemistry Department, King Fahd University of Petroleum and Minerals, Dhahran 31261, Saudi Arabia.

²Center for Research Excellence in Desalination & Water Treatment, King Fahd University of Petroleum and Minerals, Dhahran 31261, Saudi Arabia

* Corresponding author

Email: nadeembaig@kfupm.edu.sa; nadeembaig38@gmail.com

CONTENTS

Introduction

- Major sources
- History of oil spills
- Torrey Canyon oil spill
- Oil spills and Oily wastewater effects
- Cleaning & Recovery
- Selectively Superwettable porous Surfaces

Results and discussion

- Factors contributing in hydrophobic surfaces generation
- Methodology to develop Superhydrophobic surfaces
- Chemically modified mesh
- Chemically modified polyurethane

Conclusion

MAJOR SOURCES OF ORGANIC POLLUTION IN WATER

Industries According to an estimation on daily basis 33.6 million barrels oil contaminated water released

Agricultural pollution

Oil spills

Household activities

MAJOR OIL SPILLS

The Torrey Canyon Oil Spill (1967, UK)	25-36 million gallons
The Sea Star Oil Spill (1972, Gulf of Oman)	35.3 million gallons
Amoco Cadiz Oil Spill (1978, Portsall, France)	69 million gallons
Ixtoc 1 Oil Spill (1979, Gulf of Mexico)	140 million gallons
Atlantic Empress Oil Spill (1979)	90 million gallons
Nowruz Oil Field Spill (1983, Persian Gulf, Iran)	80 million gallons

MAJOR OIL SPILLS

Kolva River Oil Spill (1983, Kolva River, Russia)	84 million gallons
Odyssey Oil Spill (1988, Off the coast of Nova Scotia, Canada)	40.7 million gallons
Arabian Gulf/Kuwait (1991, Persian Gulf, Kuwait)	380-520 million gallons
M/T Haven Tanker Oil Spill (1991, Genoa, Italy)	45 million gallons
ABT Summer Oil Spill (1991, 700 nautical miles off the coast of Angola)	51-81 million gallons
Gulf oil spill (2010, Gulf of Mexico)	~206 million gallons

TORREY CANYON OIL SPILL

Torrey Canyon capacity was 60,000 to 120,000 tons of oil

Torrey Canyon was carrying the 119,000 tons of crude oil on the day of accidents

On accident more than 100,000 tonnes of crude oil spilled

on Cornwall beaches 14,250 tons of oil was treated by 10,200 tons of detergents

2 million gallons BP 1002

Used Detergents containing Aromatic hydrocarbons in high proportion about 62%

>15,000 sea birds

85% puffins killed

Effect of spills remain for years

1. Law, R. J. The Torrey Canyon Oil Spill, 1967. In Oil Spill Science and Technology; Elsevier, 2011; pp 1103–1106.
<https://doi.org/10.1016/B978-1-85617-943-0.10033-4>.
2. <https://www.bbc.com/news/uk-england-39223308>, 2017

OIL SPILLS AND OILY WASTEWATER EFFECTS

- ☐ Severely affecting the water resources
- ☐ Exposure to oil contaminated water is Jeopardizing the human and aquatic life
- ☐ Oil containing water irrigation can affect the crop production
- ☐ Volatile components increasing the atmospheric pollution
- ☐ Chemicals based cleaning of oil spilled water can further exacerbate the water and environmental pollution
- ☐ Huge quantity of chemicals are required for cleaning that make overall process expensive

Yu, L.; Han, M.; He, F. A Review of Treating Oily Wastewater. Arab. J. Chem. 2017, 10, S1913–S1922. <https://doi.org/10.1016/j.arabjc.2013.07.020>.

CLEANING & RECOVERY OF THE OIL CONTAMINATED WATER

Oil Spill Effect:

The oil contaminants may persist at the place of incidents for long time and their effect can be sensed for years. The efforts are required to clean and recover the aquatic system. The clean and recovery can be defined as in context of oil spills.

Clean

Cleaning of an ecosystem in case of oil spill can be defined as the coming back of the petroleum hydrocarbons to a level that display no detectable impact on the ecosystem.

Recovery

Recovery of an ecosystem is defined as the restoration of a biological community such as plants and animals' like before the incident are present and ecosystem start to function normally

Kingston, P. F. Long-Term Environmental Impact of Oil Spills. Spill Sci. Technol. Bull. 2002, 7 (1–2), 53–61. [https://doi.org/10.1016/S1353-2561\(02\)00051-8](https://doi.org/10.1016/S1353-2561(02)00051-8).

SELECTIVELY SUPERWETTABLE POROUS SURFACES FOR SEPARATION OF NON-POLAR ORGANIC CONTAMINANTS FROM THE WATER

Peng, Y.; Guo, Z. Recent Advances in Biomimetic Thin Membranes Applied in Emulsified Oil/Water Separation. *J. Mater. Chem. A* 2016, 4 (41), 15749–15770.

<https://doi.org/10.1039/C6TA06922C>.

RESULTS & DISCUSSIONS

CHEMICALLY MODIFIED SUPERHYDROPHOBIC SURFACES FOR
SEPARATION OF NON-POLAR CONTAMINANTS

FACTORS CONTRIBUTING IN THE GENERATION OF HYDROPHOBIC SURFACES FOR SEPARATION

- **POROUS NETWORK**

- THE DEVELOPMENT OF SUITABLE POROUS NETWORK IS MANDATORY THAT HELP IT FILTRATE OR ABSORB THE TARGETED CONTAMINANTS FROM WATER

- **SURFACE ENERGY**

- SUITABLE POROUS NETWORK MODIFICATION WITH LOW SURFACE ENERGY

- **SURFACE ROUGHNESS**

- SURFACE ROUGHNESS PLAY AN IMPORTANT ROLE TO ACHIEVE SUPERHYDROPHOBIC SURFACES

METHODOLOGY TO DEVELOP SUPERHYDROPHOBIC SURFACES

The background of the slide is a light gray gradient. It is decorated with numerous realistic water droplets of various sizes. Some droplets are large and prominent, while others are small and subtle. They are scattered across the slide, with a higher concentration in the top-left and bottom-right corners, framing the central text.

CHEMICALLY MODIFIED SUPERHYDROPHOBIC MESH

MESHES IMPORTANCE

Meshes are good choice for the separation and filtration applications for number of reasons

Meshes display good mechanical stability

Facile availability

Cost-effective

Facile surface modification

MESH INITIAL TREATMENT AND ACTIVATION

Mesh treated with several liquids

Water and acetone for cleaning

Sulfuric acid treatment to activate surface and generate surface roughness

Saleh, T. A.; Baig, N. *Prog. Org. Coatings* **2019**, 133, 27–32.
<https://doi.org/10.1016/j.porgcoat.2019.03.049>.

STAGE WISE SURFACE MORPHOLOGY OF THE MESH

1. MESH FIBER BEFORE ACID TREATMENT
2. MESH FIBERS AFTER TREATMENT TO ACHIEVE SURFACE ROUGHNESS AND ACTIVATION
3. MODIFICATION WITH LOW SURFACE ENERGY MATERIALS

MESH HYDROPHOBICITY IMPROVED BY LOW SURFACE ENERGY MATERIAL

Mesh
water
contact
Angles

(A) Before treatment

(B) After treatment

(C) After low surface energy
material modification

APPLICATION AND SEPARATION EFFICIENCY OF MESH

- THE MODIFIED MESH REPELLED WATER AND DROP OF WATER FREELY MOVED ON THE SURFACE OF THE MESH.
- THE NON-POLAR COMPONENT RAPIDLY SPREAD AND PASSED THROUGH THE PORES OF THE MESH
- THE SEPARATION EFFICIENCY FOR THE VARIOUS NON-POLAR ORGANIC COMPONENTS FROM WATER WAS ATTAINED MORE THAN 99%

Saleh, T. A.; Baig, N. *Prog. Org. Coatings* **2019**, 133, 27–32.

<https://doi.org/10.1016/j.porgcoat.2019.03.049>.

The background of the slide is a light gray gradient. It is decorated with several realistic water droplets of various sizes, primarily located in the top-left, top-right, and bottom-right corners, creating a clean, scientific aesthetic.

CHEMICAL MODIFICATION OF POLYURETHANE

POLYURETHANE ATTRACTIVE FEATURES

MODIFICATION STEPS OF POLYURETHANE

Modification steps

Cleaning of
polyurethane

Loading of
catalyst (Ferric
chloride)

Catalytic
polymerization
of pyrrole

Interaction of
the pyrrole
coated PU with
silica

Functionalization
of the surface
with the low
surface energy
materials

Saleh, T. A.; Baig, N.; Alghunaimi, F. I.; Aljurryed, N. W. RSC Adv. 2020, 10 (9), 5088–5097. <https://doi.org/10.1039/C9RA06579B>.

SEM IMAGES DESCRIBING STEPWISE SURFACE CHANGES

PU prior to modification

Step 1
Catalyst loading

Step 2

Pyrrole modification

Step 3

After Silica modification

Step 4

After low surface energy material modification

FTIR SPECTRA OF UNMODIFIED AND MODIFIED PU

PU FTIR prior to modification

PU FTIR after modification with polypyrrole, silica and Octadecyltrichlorosilane

The presence of relevant functional group absorption band has confirmed the successful functionalization of the PU surface

WATER CONTACT ANGLE BEFORE AND AFTER MODIFICATION

Water contact angle before modification

Water contact angle after modification

Saleh, T. A.; Baig, N.; Alghunaimi, F. I.; Aljurryyed, N. W. RSC Adv. 2020, 10 (9), 5088–5097.

<https://doi.org/10.1039/C9RA06579B>.

ABSORPTION CAPACITY OF MODIFIED POLYURETHANE FOR VARIOUS NON-POLAR COMPONENTS

Saleh, T. A.; Baig, N.; Alghunaimi, F. I.; Aljurryyed, N. W. RSC Adv. 2020, 10 (9), 5088–5097.

<https://doi.org/10.1039/C9RA06579B>.

SEPARATION OF SURFACTANT FREE EMULSIONS (WATER IN OIL)

Emulsion

Separation

After Separation

Saleh, T. A.; Baig, N.; Alghunaimi, F. I.; Aljurryed, N. W. RSC Adv. 2020, 10 (9), 5088–5097.

<https://doi.org/10.1039/C9RA06579B>.

FASCINATING FEATURE OF CHEMICALLY MODIFIED POLYURETHANE

- ❑ MODIFIED POLYURETHANE HAS DISPLAYED ABSORPTION CAPACITY IN THE RANGE OF 18 TO 34 TIMES TO ITS OWN WEIGHT
- ❑ EXCELLENT REGENERATION FOR HEXANE (RSD= ± 0.7) , DODECANE(± 1.2) AND PETROL (± 2.9)
- ❑ MODIFIED POLYURETHANE HAS REVEALED HIGH FLUX FOR HEXANE
- ❑ MODIFIED POLYURETHANE IS EFFECTIVE FOR THE SEPARATION OF THE EMULSIONS

CONCLUSION

Meshes are mechanically stable

Activation of mesh surface achieved through facile method

Modification process is easy

Meshes can only used for filtration process

Polyurethane provide opportunity for both absorption and separation application

Chemically modified surfaces of mesh and polyurethane selective towards non-polar organic contaminates from water

These materials are Cost-effective and provide chances for scale up

ACKNOWLEDGEMENT

Authors gratefully acknowledge the support provided by the **“King Fahd University of Petroleum and Minerals, Dhahran, Saudi Arabia”**.