The Relevance of ATR-FTIR Spectroscopy in Semiconductor Photocatalysis

---

Mohamed Faycal Atitar, Hamza Belhadj,
Ralf Dillert and Detlef W. Bahnemann

Additional information is available at the end of the chapter

<http://dx.doi.org/10.5772/60887>

Abstract

Attenuated total reflection Fourier-transform infrared (ATR-FTIR) spectroscopy has a high potential for investigating a wide range of samples and systems. In photocatalysis, various interfacial phenomena can be studied using this technique, including pH-dependent adsorption and photodegradation of probe molecules. The analysis of the processes occurring at the interface of thin particle films deposited on the surface of an ATR crystal, either in the liquid or the gas phase, is perhaps the best way to elucidate the mechanism of adsorption and heterogeneous photocatalytic reactions. This chapter summarizes the recent advances and applications of ATR-FTIR techniques in semiconductor photocatalysis. A brief outlook at some of the possible investigations in this area is provided and the different proposed adsorption and photocatalytic degradation mechanisms are discussed.

Keywords: Adsorption, attenuated total reflection Fourier-transform infrared (ATR-FTIR), photocatalysis, semiconductor, spectroscopy, thin films, TiO₂

---

1. Introduction

The expanding interest in environmental and energy issues led to the consideration of heterogeneous photocatalysis as one of the most promising advanced oxidation processes. The interest in this scientific field has increased in the last decade since photocatalysis is assumed to be a powerful tool for the destruction and remediation of highly toxic pollutants, the

---

purification of polluted water and air, the development of self-cleaning surfaces coated with semiconducting metal oxide materials, and the conversion of solar energy into chemical energy [1–3]. Many semiconductor materials have been tested as photocatalysts, nevertheless, due to its low cost, abundance, high activity, and stability under a variety of conditions. Titanium dioxide (TiO_2) is the most reliable and widely used material [4, 5]. Accordingly, there has been a tremendous amount of research on diverse aspects of TiO_2 (nano)materials, ranging from their synthesis, characterization, and applications to atomic scale, to experimental and theoretical investigations of their fundamental physical and chemical properties [1, 5–7]. Despite these investigations, there remains a need to better understand the reaction mechanisms of the transformation of organic molecules occurring during TiO_2 photocatalysis.

Surface science plays a prominent role in mechanistic investigations concerning the photocatalytic process, providing a unique approach to understand bulk, surface, and interfacial phenomena occurring at the TiO_2 surface [6, 8, 9]. According to several proposed photocatalytic mechanisms [10, 11], an important point for the conversion of the molecules on TiO_2 is the physical and electronic structure of the adsorbed state of the molecules. How a molecule binds onto the TiO_2 surface influences its electronic structure, as well as its redox properties. *Inter alia*, coverage, thermal stability, and reactivity, adsorption structure and site, are all important factors [8]. The interest in surface techniques to investigate liquid-solid and gas-solid interfacial chemistry has grown due to the importance of the information they provide. Few surface spectroscopic techniques are adequate to perform *in situ* analyses of interfacial interactions. For example, sum-frequency vibrational spectroscopy is restricted to planar solid-solution interfaces [12], infrared ellipsometry is considered mainly as a technique for the analysis of thin solid films rather than of interfacial species [13], and surface enhanced Raman spectroscopy (SERS) requires the presence of metals on the surface. Thus, this complicates the more widespread applicability of SERS [14, 15].

IR spectroscopy is the oldest and most commonly used method for identifying both organic and inorganic chemicals, as well as for providing specific information on molecular structure, chemical bonding, and molecular environment. Being a powerful tool for qualitative and quantitative studies, it can be applied to study solids, liquids, or gaseous samples [16]. Recently, IR spectroscopy has been applied *in situ* to study surface reactions on immersed solids such as oxides. This has been achieved with particle films via internal reflection or attenuated total reflection (ATR-FTIR) methods. Investigating several metal oxide solid particles in suspensions or deposited as thin films on ATR crystals, these developments have led to *in situ* ATR-FTIR studies of adsorption and chemical reactions on a variety of solid-liquid and/or solid-gas interfaces in the photocatalysis context [17–24]. The ATR-FTIR technique has proved to be a powerful tool for probing binding mechanisms and for characterizing the adsorption of organic molecules onto metal oxide surfaces in liquid media.

This book chapter focuses on the application of this technique in the above-mentioned context. An overview of the investigations that have been performed to date will be given, analyzing the different experimental procedures, and summarizing the performed investigation of

surface interactions. An in-depth analysis of the different proposed adsorption and photocatalytic reaction mechanisms on TiO_2 as well as on other metal oxides also employed in photocatalysis will be given. To complement this overview, results and interpretations of quantum chemical calculations will also be presented.

2. History and brief overview of ATR-FTIR spectroscopy

Infrared absorption spectroscopy (IR) has contributed for more than fifty years to the molecular view on a wide variety of systems. The selection rule for a vibrational mode of a molecule to be IR active is that there is a change of the electric dipole moment of the molecule upon absorption of light. The absorption of infrared light due to the excitation from the ground vibrational energy level to a higher energy level provides information concerning molecular structure and molecular interactions [15, 25, 26]. Due to the existence of the wide absorption spectra database in the mid-infrared region ($4000\text{--}400\text{ cm}^{-1}$), infrared spectroscopy is considered as a universal technique since many molecules have strong absorbances in this region [27].

Fourier-transform infrared (FTIR) spectroscopy is a well-established technique based on the idea of the interference of radiation between two beams to yield an interferogram. The latter is a signal produced as a function of the change of path length between the two beams. The two domains of distance and frequency are interconvertible by the mathematical Fourier transformation method.

ATR spectroscopy was introduced simultaneously by Harrik [28] and Fahrenfort [29] based upon the total internal reflection phenomena. In this approach, IR spectra are recorded for a sample material that is in contact with an internal reflection element (IRE). The IR beam is focused onto the edge of the IRE, reflected through the IRE, and then directed to the detector (cf. Figure 1) [26, 27]. In this case, all the light reflects off the internal surface of the IRE, hence explaining the term total internal reflection [27]. The internal reflection element (IRE) or ATR crystal has, in most cases, a higher refractive index (n_1) as compared to the sample (n_2). Another important parameter is the incidence angle θ that can be determined from the refractive indexes of the sample (n_2) and the IRE (n_1):

$$\theta = \sin^{-1}\left(\frac{n_2}{n_1}\right) \quad (1)$$

The major applications of the ATR method are in the mid-IR region. However, the range has been extended to the near-IR, the far-IR, as well as to the UV and visible spectral regions. Therefore, it is of great importance to choose a suitable ATR crystal for a given application. The most common ATR crystals with their respective refractive indexes and some other relevant properties are summarized in Table 1.

Figure 1. Schematic diagram of a horizontal ATR sampling accessory illustrating the important parameters [16].

Material	Refractive index	Wavenumber range (cm ⁻¹)	d _p (μm)	References
Diamond	2.4	45000–2500	1.35–1.66	[30][31][32]
Germanium (Ge)	4	5500–870	0.65–0.73	[30][31][32]
Zinc Selenide (ZnSe)	2.41	20000–650	1.22–1.66	[30][31][32]
AMTIR (As/Ge/Se glass)	2.5	11000–750	1.46	[30]
Silicon (Si)	3.4	-	0.84–1.17	[30][32]
Thallium bromide (KRS-5)	2.37	20000–250	1.22–1.73	[30][32]
Cd telluride (CdTe)	2.67	10000–450	-	[31]
Sapphire (Al ₂ O ₃)	1.74	25000–1800	-	[31]
Zinc Sulfide (ZnS)	2.2	17000–950	2.34	[31][32]
Cubic Zirconia (ZrO ₂)	2.15	25000–1800	-	[31]

Table 1. Relevant properties of some common ATR crystals.

Since the IR beam should penetrate the sample, the penetration depth (d_p) is one of the important parameters in ATR-FTIR spectroscopy. The measure of the depth that the infrared beam enters into the sample is defined by equation (2):

$$d_p = \frac{1}{\left[2\pi W n_1 \left(\sin^2 \theta - n_{21}^2 \right)^{\frac{1}{2}} \right]} \tag{2}$$

where d_p is the depth of penetration, W the wavenumber, n_1 the refractive index of the ATR crystal, θ the angle of incidence, and n_{21} the fraction $\frac{n_2}{n_1}$.

Each of the parameters mentioned above has important messages to teach us about the ATR technique and its application. Readers interested in details of the theory of ATR should consult the respective literature [16, 25, 27].

3. Experimental processing

One of the advantages of the ATR-FTIR technique is that an experiment can be easily conducted to study the interactions between a chosen probe molecule and the surface of different metal oxides. The whole procedure consists in the preparation of a thin film of nanoparticles of the chosen metal oxide on the ATR crystal. This thin film should be stable, at least during the experiment, and its thickness should allow the penetration of the IR beam to reach the interface, e.g., the sample solution above the oxide layer. A thin homogeneous layer of the nanoparticles on the ATR crystal is generally produced from their suspension in an adequate solvent. This suspension is carefully drop-casted on the IRE material. Examples of the preparation of these thin layers, especially those made of TiO_2 , can be found elsewhere [18, 19, 23, 33].

It is worth noting that the contact between the probe molecule and the layer can lead to a change in some operational parameters such as pH, temperature, and ionic strength of the supernatant solution. Therefore, studies on adsorption phenomena are better carried out employing flow cell reactors either in the liquid or the gas phase (see Figure 2a) where the solution or the dispersant circulate continuously over the layer. This allows the control of the above-mentioned parameters and the monitoring of the evolution in time of the system under different conditions. As an alternative, a sample batch system can also be employed where the inlet and outlet are closed (Figure 2b) [23].

Figure 2. Flow cell reactor for ATR-FTIR spectroscopic studies (Reproduced from [23] with permission of the PCCP Owner Societies).

Prior to coating the ATR crystal, a spectrum of the blank ATR crystal is collected for spectral processing. Mainly, two different approaches can be used for the spectral processing. The first one is the normalization of the spectra of the ligand to that of the matrix (solvent at the pH of interest in the liquid phase or dispersant in the gas phase) from which a spectrum is collected. The probe molecule is then introduced and the corresponding spectrum is collected. The spectrum of the probe molecule is then referenced to the background spectrum (solvent/dispersant). The second approach is as follows: after preparing the thin film, a spectrum of the solvent at the pH of interest (or of the dispersant in the gas phase) is collected; the probe molecule is introduced and a spectrum is collected; the single beam spectrum of both solvent/dispersant and of the probe molecule in the solvent/dispersant is referenced to the blank ATR crystal to obtain the absorbance spectra of each. Subsequently, the absorbance spectrum of the solvent/dispersant is subtracted from the spectrum of the probe molecule. To collect spectra for the probe molecule alone the same experimental process is used but without the nanoparticle thin layer [30].

4. Probing interfacial reactions by ATR-FTIR investigations

4.1. Metal oxide-water interface

Considering its relevance to semiconductor photocatalysis, water splitting, and other important applications, the interaction of water with metal oxide surfaces, especially TiO_2 , has been the focus of several experimental and theoretical investigations over the last decades [3, 4, 6, 8, 34–36]. Molecular, dissociated, and undissociated states of water adsorbed at a solid surface have been suggested. In addition to that, a mixture of these adsorption states is possible.

ATR-FTIR spectroscopy is one of the suitable techniques to investigate the adsorption of water molecules on a metal oxide surface under a wide range of conditions [37–39]. From many perspectives, numerous experimental and theoretical water adsorption studies have been conducted by means of ATR-FTIR spectroscopy [17, 37, 40, 41].

Figure 3 depicts the typical spectra of water adsorbed on TiO_2 (anatase/rutile Evonik-Degussa Aeroxide TiO_2 P25) [38]. The broad absorption band at around $3600\text{--}2800\text{ cm}^{-1}$ and the small peak at 3696 cm^{-1} are well-known to be the stretching vibration modes of the H_2O molecules, which have complex interactions through hydrogen bonds, and the end part of polymerically chained H_2O molecules without hydrogen bonds, respectively. The broad band contains not only the components of the H_2O molecules with different numbers of hydrogen bonds but also the Fermi resonance attributed to the overtone absorption of the bending mode $\delta(\text{H}_2\text{O})$ at 1637 cm^{-1} . Therefore, it is difficult to analyze the detailed adsorption state of the polymerically chained H_2O molecules on metal oxide surfaces only from FTIR (mid-infrared) measurements [38]. However, based on the information obtained from such IR spectra, ATR-FTIR spectroscopy has been used for the characterization and identification of intermediate mechanisms involved in environmental interfaces [42], mainly during photocatalytic oxidation processes induced at the TiO_2 -water interface [37,40].

Figure 3. FT-IR (MIR) absorption spectra of TiO_2 (Evonik-Degussa Aeroxide TiO_2 P25) in air (a) and after evacuation at room temperature for 1 h (b) (Reprinted with permission from Takeuchi M, Martra G, Coluccia S, Anpo M. Investigations of the Structure of H_2O Clusters Adsorbed on TiO_2 Surfaces by Near-Infrared Absorption Spectroscopy. *Journal of Physical Chemistry B*; 109(15):7387–91. Copyright (2005) American Chemical Society).

Starting from the hypothesis that adsorbed H_2O changes its conformation due to the co-adsorption of cyclohexane on TiO_2 (anatase, Sachtleben Hombikat UV100), Almeida et al. [40] have shown with the help of additional DFT (Density Functional Theory) calculations, yielding the adsorption energy and the structure of the water molecule at different hydration levels (Figure 4), that at least three layers of water are formed during the adsorption process. The first layer includes only chemisorbed H_2O molecules. The second hydration level includes physisorbed (H-bonded) H_2O molecules on surface OH sites, and the highest hydration level contains an additional adsorbed water layer. The dissociative chemisorption of water is assumed to be energetically favored. In addition to that, dissociative chemisorption of water generates at least two different Ti-OH groups. At least one of these two new OH sites contains an oxygen atom originally originating from the TiO_2 lattice structure [40]. This finding allowed the authors to provide a spectral and structural interpretation of the mode of adsorption of cyclohexanone on the hydrated TiO_2 surface [40].

Besides of that, several research reports have identified and specified the different bending modes and structures of water on the TiO_2 surface during, before, and after UV light irradiation. It has been reported that UV irradiation induces a structural ordering of the adsorbed water layer [43], or results in an increase in the amount of surface OH groups, thus increasing the hydrophilicity of the TiO_2 surface [44]. Mendive et al. [37] have revealed by ATR-FTIR studies that the disaggregation of particle agglomerates plays an important role in UV illuminated aqueous TiO_2 nanoparticulate systems.

However, it should be noted here that the exact nature of the adsorption of water is still a matter of discussion in the field of metal oxide (especially of TiO_2) photocatalysis. This is a

	(100)	(101)	(001)
Structures			
Hydration ($\text{H}_2\text{O}/\text{nm}^2$)	6.2	4.8	2.3
Energy (kJ/mol)	-68.5	-65.7	-184.7
Structures			
Hydration ($\text{H}_2\text{O}/\text{nm}^2$)	9.3	9.6	7.0
Energy (kJ/mol)	-61.7	-67.1	-97.4
Structures			
Hydration ($\text{H}_2\text{O}/\text{nm}^2$)	18.5	16.8	16.4
Energy (kJ/mol)	-61.0	-57.1	-72.6

Figure 4. Adsorption energies and structures of H_2O on TiO_2 (100), (101), and (001) facets, at different hydration levels (Reprinted with permission from Almeida A, Calatayud M. Combined ATR-FTIR and DFT Study of Cyclohexanone Adsorption on Hydrated TiO_2 Anatase Surfaces. *Journal of Physical Chemistry C*; 115(29):14164–14172. Copyright (2011) American Chemical Society).

consequence of the diverse possibilities of interpretation arising from the combination of experimental results obtained by ATR-FTIR spectroscopy and by other techniques. Obviously, there is not yet a general consensus on the mechanism of adsorption of water on TiO_2 .

4.2. Interactions of probe molecules with the metal oxide surface

ATR-FTIR spectroscopy yields important insight into the surface speciation of probe molecules adsorbed on nanomaterials [30]. Chemical or inner sphere adsorption is generally studied when it is expected that the probe molecule is able to coordinate with the metal ions of the substrate covering the ATR crystal [15].

Investigations of the interaction of a large number of ligands on metal oxide, metal hydroxide, and metal oxyhydroxide systems have been performed employing ATR-FTIR spectroscopy [26]. The objective of these investigations is to obtain an insight into the chemical nature of these interactions, being either qualitative such as the mode of adsorption and the surface speciation, or quantitative such as the kinetics and the surface coverage.

It is worth to note that TiO_2 nanoparticles are much more extensively used as substrates as compared with other metal oxides. The adsorption of organic compounds bearing common functional groups such as acids [23, 45, 46], amino acids [47], phenolic compounds [11, 48], and a few complex heteroaromatic compounds [49–52] has been studied in detail (cf. Table 3).

As an example, a typical ATR-FTIR spectrum of an aqueous solution of the herbicide imazapyr in the absence and presence of a TiO_2 layer is presented in Figure 5. The reliability of information obtained from the IR spectra is dependent mainly upon the correct assignment of the vibrational modes by comparison with published spectroscopic data [15, 30]. Mudunkotuwa et al. have presented a summary of several common IR absorption band frequencies (Table 2) [30]. Furthermore, the infrared spectral data collected for coordination compounds [53] are very useful when interpreting the spectra of adsorbates, which mostly resemble those of ligands of coordination compounds [15]. In addition to that, the interpretation of the increase in the intensities of the bands of functional groups, as well as the shifting of these bands either to the blue or to the red spectral regions also provide important information concerning the type of interaction between adsorbate and surface. The interpretation of IR bands is very helpful for a qualitative analysis, e.g., concerning the points of interactions, the modes of adsorption, and the molecular speciation, respectively.

Figure 5. ATR-FTIR spectra of 8×10^{-3} mol L^{-1} imazapyr aqueous solution at pH 3 (dashed lines); and 2×10^{-3} mol L^{-1} imazapyr aqueous solution in contact with a TiO_2 film (solid lines). Reference spectra were of water in contact with the bare ZnSe prism and of the bare TiO_2 film respectively [54].

As mentioned above, the complexity of the obtained IR spectra usually requires the combination of different techniques to enable their interpretation. Generally, the deductions resulting from the analysis of the IR spectra have to be supported by the results of other experimental techniques and/or by theoretical calculations. Several experimental and theoretical studies on the adsorption of aliphatic mono- and di-carboxylic acids on metal oxide surfaces have been performed [46]. It is assumed that the binding of carboxylates at the solid metal oxide surface occurs in several ways such as physisorption through electrostatic attraction and hydrogen bonding, and chemisorption in different modes including monodentate, bridged bidentate, and chelating bidentate adsorbed structures [55–57]. These different binding modes can be

Vibrational Mode	Wavenumber (cm ⁻¹)
$\nu(\text{C=O})$	1730–1720
$\nu_{\text{asym}}(\text{COO}^-)$	1620–1590
$\nu_{\text{sym}}(\text{COO}^-)$	1410–1390
$\delta_{\text{asym}}(\text{NH}_3^+)$	1630
$\delta_{\text{sym}}(\text{NH}_3^+)$	1571
$\nu_{\text{asym}}(\text{CH}_2)$	2920
$\nu_{\text{sc}}(\text{CH}_2)$	1442–1438
$\nu_{\text{w}}(\text{CH}_2)$	1400–1200
$\nu_{\text{t}}(\text{CH}_2)$	730–720
$\nu_{\text{sym}}(\text{NH})$	3300–3100
$\nu_{\text{sym}}(\text{C=O})^{\text{major}} + \nu_{\text{sym}}(\text{C-N})^{\text{minor}}$	1700–1600 (Amide I)
$\nu_{\text{sym}}(\text{C-N}) + \delta(\text{N-H})_{\text{out of phase}}$	1580–1510 (Amide II)
$\nu_{\text{sym}}(\text{C-N}) + \delta(\text{N-H})_{\text{in phase}}$	1400–1200 (Amide III)

Table 2. IR absorption frequencies of common organic functional groups (Adapted from [30] with permission of The Royal Society of Chemistry).

distinguished in an infrared spectrum by the difference $\Delta\nu_{\text{a-s}}$ of the frequencies of the asymmetric and the symmetric mode of the carboxylate stretching vibration. By comparing the $\Delta\nu_{\text{a-s}}$ of free aqueous carboxylate, $\Delta\nu_{\text{a-s}}(\text{free})$, to the $\Delta\nu_{\text{a-s}}(\text{adsorbed})$ values measured in transition metal complexes, the following correlations were found [46, 56, 58]:

$\Delta\nu_{\text{a-s}}(\text{adsorbed}) > \Delta\nu_{\text{a-s}}(\text{free})$: monodentate coordination

$\Delta\nu_{\text{a-s}}(\text{adsorbed}) < \Delta\nu_{\text{a-s}}(\text{free})$: bidentate chelating or bridging

$\Delta\nu_{\text{a-s}}(\text{adsorbed}) \ll \Delta\nu_{\text{a-s}}(\text{free})$: bidentate chelating, unless short metal-metal bonds are present

DFT calculations have been performed by Vittadini et al. for several possible adsorption conformations of formic acid and sodium formate on the anatase surface to support the interpretation of ATR-FTIR spectra measured of formic acid adsorbed on the TiO_2 surface [59]. The comparison of the calculated results with this experimental information enabled the identification of seven different surface species (see Figure 6). On the hydrated surface, both HCOOH and HCOONa preferentially form inner-sphere adsorption complexes. HCOOH as monodentate adsorbate dissociates due to the interaction with a nearby water molecule, while HCOONa prefers a bridging bidentate structure [59].

Mono-carboxylic acids, i.e., formic and acetic acid, were found to bind on ZrO_2 and Ta_2O_5 surfaces in both protonated and deprotonated carboxylic acid forms indicating a bridging bidentate adsorption. Under the experimental conditions of this work no adsorption of formic acid onto TiO_2 and Al_2O_3 was observed [46].

Figure 6. Possible configurations for HCOOH and HCOO^- species bound to metal cations (Reprinted with permission from Vittadini A, Selloni A, Rotzinger FP, Grätzel M. Formic Acid Adsorption on Dry and Hydrated TiO_2 Anatase (101) Surfaces by DFT Calculations. *Journal of Physical Chemistry B*; 104(101):1300–1306. Copyright (2000) American Chemical Society).

Dicarboxylic acids adsorb much more strongly to oxide surfaces than mono-carboxylic acids due to both electrostatic and chemical interactions.

Oxalic acid is one of the most investigated molecules in this regard [18, 45, 58, 60, 61]. Based on a series of spectra recorded at varying different experimental parameters (concentration, pH, and ionic strength), and supported by the comparison of these spectra with those of the aqueous $[\text{Fe}(\text{Ox})_y]_z$ complex, Hug et al. [18] described several surface complexes formed during the adsorption of oxalic acid at the TiO_2 P25 surface. The obtained data strongly support the assumption that oxalate forms specific inner-sphere coordination complexes with surface Ti^{4+} sites. These complexes are formed through bidentate bridging or monodentate bending modes.

Mendive et al. have published several papers presenting experimental results of their investigation of the TiO_2 -oxalic acid system using both pure anatase and rutile phases. In addition to that, data of quantum chemical calculations using Modified Symmetrically Orthogonalized

Intermediate Neglect of Differential Overlap (MSINDO) have been presented to yield a complete insight into the TiO_2 -oxalate system [23, 24, 62, 63]. A detailed analysis of the experimental ATR-FTIR data and the data obtained from theoretical calculations (IR spectra (Figure 7) and calculated bending energies) has led to the suggestion of different adsorbate structures of oxalic acid either on anatase or on rutile nanoparticles (Figure 8). By comparison between both TiO_2 phases (anatase and rutile), the difference as well as the similarity in the adsorption of oxalate can be explained either by the mode of adsorption, the structure of the surface complexes, the surface speciation of either TiO_2 phases, or the adsorption energies.

Young et al. [45] have published the results of an ATR-FTIR study focused on the adsorption-desorption kinetics of oxalic acid on the anatase TiO_2 surface. The measured spectra were not found to be well resolved. However, based on the absorbance versus time behavior, the authors were able to extract the pseudo-first-order rate constants corresponding to the three expected adsorbed species of oxalic acid at the TiO_2 surface.

Furthermore, Mendive et al. [61] have proposed the mechanism of the photocatalytic degradation of oxalic acid with the help of the above mentioned experimental and theoretical investigations [24, 63]. The possible pathways for the formation of oxalic acid photoproducts, as well as the role of the TiO_2 surface as active surface have been discussed in detail [61]. An example of the proposed degradation pathways of the oxalic acid surface complexes is depicted in Figure 9.

Figure 7. Experimental and calculated FTIR spectra of oxalic acid on anatase (Reproduced from [23] with permission of the PCCP Owner Societies).

Figure 8. Adsorbed structures of oxalic acid on anatase (A) (Reproduced from [24] with permission of the PCCP Owner Societies) and Rutile (B) (Reproduced from [63] with permission of the PCCP owner Societies) in equilibrium in the dark. A scheme of every structure is provided. Ti, O, H and C atoms are represented by large light, dark, small light and dark-dashed spheres respectively.

As mentioned in the introduction of this chapter, the direct evidence for the formation of structurally different surface complexes is an important step in the understanding of metal oxide photocatalysis, especially of TiO₂ photocatalysis. This is due to the fact that the reactivity and the pathways for product formation are determined by the structures of the formed surface species during the dark adsorption. Recently, Montoya et al. [11] have investigated the interaction of the TiO₂ surface with three probe molecules, *e.g.*, formic acid, benzene, and phenol employing ATR-FTIR spectroscopy. Based upon the analysis of the IR spectra (Figure 10), assumptions have been made concerning the physisorption of benzene (no changes have been observed in the spectra with and without the TiO₂ layer), the strong chemisorption of formic acid, and also the role of the solvent (water or acetonitrile) for the adsorption mode of phenol. Based on these results, the authors provided an insight into the mode of interaction of the probe molecules with the TiO₂ surface (chemisorption or physisorption) (Figure 11). In addition to that, they discussed the photocatalytic oxidation mechanism induced either by the

Figure 9. Possible photocatalytic degradation pathways of species adsorbed on anatase (Reprinted from Oxalic Acid at the TiO₂/Water Interface under UV(A) Illumination: Surface Reaction Mechanisms, Cecilia B. Mendive, Thomas Bredow, Jenny Schneider, Miguel Blesa, Detlef Bahnemann. *Journal of Catalysis* 2015, 322:60-72, Copyright (2015), with permission from Elsevier).

reaction of surface trapped holes with the adsorbate (direct pathway) or the reaction of photocatalytically generated $\cdot\text{OH}$ radicals with the physisorbed molecules (indirect pathway). The authors concluded that formic acid is directly oxidized due to its strong chemisorption onto the TiO₂ surface, while physisorbed benzene is indirectly oxidized. For phenol the authors suggested a combination of both pathways [10, 11].

Figure 10. ATR-FTIR spectra of: A) a 100 mM solution of acetonitrile dissolved phenol, in the absence (a) and in the presence of an anatase film under different TiO_2 -Phenol contact times (b-d); B) a 100 mM solution of water dissolved phenol (pH 3) in the absence (a) and in the presence of a TiO_2 anatase film, under different TiO_2 -Phenol contact times (b-d); C) a 3365 mM solution of acetonitrile dissolved benzene in absence (a) and presence of a TiO_2 anatase film under different TiO_2 -Benzene contact times (b-c) (Reprinted with permission from Montoya JF, Atitar FM, Bahnemann DW, Peral J, Salvador P. Comprehensive Kinetic and Mechanistic Analysis of TiO_2 Photocatalytic Reactions According to the Direct-Indirect (DI) Model: II) Experimental Validation. *Journal of Physical Chemistry C*; 28(118):14276–14290. Copyright (2014) American Chemical Society).

In addition to the presented examples, several experimental and theoretical studies have been performed concerning the adsorption and various photocatalytic reactions by means of the ATR-FTIR technique. Table 3 presents a survey of published data on the adsorption as well as

Figure 11. Interaction modes of benzene, formic acid and phenol, model organic compounds with the TiO_2 surface (Reprinted with permission from Montoya JF, Atitar FM, Bahnemann DW, Peral J, Salvador P. Comprehensive Kinetic and Mechanistic Analysis of TiO_2 Photocatalytic Reactions According to the Direct-Indirect (DI) Model: II) Experimental Validation. *Journal of Physical Chemistry C*; 28(118):14276–90. Copyright (2014) American Chemical Society).

the photooxidation of aqueous organic compounds on metal oxide surfaces studied by means of ATR-FTIR spectroscopy.

Adsorbate or reactant	Material	Study	Ref
Acetic acid	Rutile	Adsorption	[64]
Acetate	Rutile	Adsorption	[65]
Acrylic acid	P25	Adsorption	[66]
Poly(Acrylic acid)	Hematite	Adsorption	[67]
L- α -alanine	P25	Adsorption	[68]
Amino acid	P25 Au/ TiO_2	Photo-Oxidation	[69]
p-Arsanilic acid	Iron-(Oxyhydr)Oxides	Adsorption	[70],[71]
Aspartic acid	TiO_2 (synthesis)	Adsorption	[72]
Benzoic acid / benzoate	Aluminum Hydroxide	Adsorption	[73]
Boric acid	Hydrous Ferric Oxide	Adsorption	[74]
Catechol	P25	Photo-Oxidation	[75]
		Adsorption	[76]
	TiO_2 (synthesis)	Adsorption	[48]
	Cr_2O_3	Adsorption	
	MnO_2	Adsorption	
	Fe_2O_3	Adsorption	
4-Chlorocatechol	P25	Adsorption	[77]
Citric acid	Rutile	Adsorption	[64]

	Anatase		[78]
<i>m</i> -Cresol	P25	Adsorption	[76]
<i>o</i> -Cresol			
Cyclohexane	UV100	Adsorption Photo-Oxidation	[33],[79]
Cyclohexanone	TiO ₂ (synthesis)	Adsorption	[80]
Cysteine	P25	Adsorption	[47]
Dextrin	Anatase	Adsorption	[22]
Dicarboxylates	Fe(III)(hydr)oxides	Photo-Oxidation	[81]
α -hydroxydicarboxylates			
Dihydroxyphenylalanine	Rutile	Adsorption	[82]
Dimethylarsinic acid	Iron-(Oxyhydr)Oxides	Adsorption	[70]
<i>E. Coli</i>	P25	Photo-Oxidation	[83]
Ethanol	TiO ₂ (synthesis)	Photo-Oxidation	[84]
Formic acid	Rutile	Adsorption	[64]
	TiO ₂ (synthesis)		[55]
Formate	Rutile	Adsorption	[65]
Fumaric acid	Hematite	Adsorption	[85]
Gallic acid	P25	Photo-Oxidation	[86]
Glutamic acid	TiO ₂ (synthesis)	Adsorption	[72]
Glyoxylic acid	P25	Adsorption	[87]
Isopropyl	P25	Adsorption	[88]
Methylphosphonofluoridate		Photo-Oxidation	
Lactic acid	P25	Adsorption	[66]
Maleic acid	Hematite	Adsorption	[85]
Malonate	Rutile	Adsorption	[58]
	Anatase		
Malonic acid	Au/TiO ₂ (synthesis)	Photo-Oxidation	[89]
	P25		[90]
Nicotinic acid	TiO ₂ (synthesis)	Adsorption	[51]
Nitrate	Al ₂ O ₃	Adsorption	[91]
<i>o</i> -Phthalic acid	Hematite	Adsorption	[92]
Oxalate	Anatase	Adsorption	[58]
	Rutile		
Oxalic acid	Anatase	Photo-Oxidation	[61]
	Rutile	Adsorption	[45]
	Anatase		

Phenol	Anatase	Adsorption	[11]
	P25	Photo-Oxidation	[93]
4,4'-Bis(2-sulfostyryl)biphenyl	Rutile	Photo-Oxidation	[94]
	Anatase		
	Hematite		
	δ-Alumina		
	Lepidocrocite		
β-Picoline	TiO ₂ (synthesis)	Adsorption	[51]
Polyacrylates	Hematite	Adsorption	[95]
1,2-propylene glycol	P25	Photo-Oxidation	[93]
Pyridine	P25	Adsorption	[96]
Pyruvic Acid	P25	Adsorption	[66]
Pyridine-3-carbaldehyde	TiO ₂ (synthesis)	adsorption	[97]
			[51]
Ru-bpy	TiO ₂ (synthesis)	Adsorption	[98]
Succinate	Rutile	Adsorption	[58]
	Anatase		
	Lepidocrocite		
Succinic acid	Hematite	Adsorption	[85]
	P25	Photo-Oxidation	[90]
Toluene	TiO ₂ (synthesis)	Photo-Oxidation	[99]
	P25-TiO ₂		[100]

Table 3. Selection of previously published ATR-FTIR studies concerning the adsorption and photooxidation of common ligands on metal oxides surfaces.

5. Concluding remarks

The ATR-FTIR technique offers the chance to obtain novel information concerning interfacial processes *in situ*. This information can be used to explain surface reaction mechanisms. Hence, ATR-FTIR studies are becoming increasingly popular as an investigative technique and may now be considered as one tool of choice in the field of interfacial chemistry when compared to other techniques, particularly in obtaining data under ambient conditions. This is due to the major advantages of ATR-FTIR spectroscopy such as the *in situ* data collection, as well as the high sensitivity, simplicity, and rapidity of the measurements.

The use of ATR-FTIR in the area of photocatalysis is of great importance since it provides both qualitative and quantitative molecular insight into interfacial processes occurring in the dark (adsorption) and under UV illumination (adsorption/desorption and chemical reactions). The information obtained will often be the key for a deeper understanding of the mechanisms occurring in metal oxide photocatalysis.

Acknowledgements

The present study was performed within the project “Establishment of the Laboratory of Photoactive Nanocomposite Materials” (No. 14.750.31.0016) supported by a Grant from the Government of the Russian Federation. M. Faycal Atitar gratefully acknowledges a scholarship from the DAAD in the Frame of a Sandwich-Program.

Author details

Mohamed Faycal Atitar^{1*}, Hamza Belhadj¹, Ralf Dillert¹ and Detlef W. Bahnemann^{1,2}

*Address all correspondence to: bahnemann@iftc.uni-hannover.de

1 Institut fuer Technische Chemie, Leibniz Universitaet Hannover, Hannover, Germany

2 Laboratory of Photoactive Nanocomposite Materials, Department of Photonics, Faculty of Physics, Saint-Petersburg State University, Saint-Petersburg, Russia

References

- [1] Hoffmann MR, Martin ST, Choi W, Bahnemann DW. Environmental Applications of Semiconductor Photocatalysis. *Chemical Reviews* 1995;95(1):69–96.
- [2] Schneider J, Matsuoka M, Takeuchi M, Zhang J, Horiuchi Y, Anpo M, Bahnemann DW. Understanding TiO₂ Photocatalysis: Mechanisms and Materials. *Chemical Reviews* 2014;114: 9919–9986.
- [3] De Angelis F, Di Valentin C, Fantacci S, Vittadini A, Selloni A. Theoretical Studies on Anatase and Less Common TiO₂ Phases: Bulk, Surfaces, and Nanomaterials. *Chemical Reviews* 2014;114(19):9708–9753.
- [4] Linsebigler A, Lu G, Jr JY. Photocatalysis on TiO₂ Surfaces: Principles, Mechanisms, and Selected Results. *Chemical Reviews* 1995;95:735–758.
- [5] Hashimoto K, Irie H, Fujishima A. TiO₂ Photocatalysis: A Historical Overview and Future Prospects. *Japanese Journal of Applied Physics* 2006;44(12):8269–8285.
- [6] Diebold U. The Surface Science of Titanium Dioxide. *Surface Science Reports* 2003;48(5-8):53–229.
- [7] Ismail AA, Bahnemann DW. Photochemical Splitting of Water for Hydrogen Production by Photocatalysis: A Review. *Solar Energy Materials and Solar Cells* 2014;128:85–101.

- [8] Henderson MA. A Surface Science Perspective on TiO₂ Photocatalysis. *Surface Science Reports* 2011;66(6-7):185–297.
- [9] Fujishima A, Zhang X, Tryk D. TiO₂ Photocatalysis and Related Surface Phenomena. *Surface Science Reports* 2008;63(12):515–582.
- [10] Montoya JF, Peral J, Salvador P. Comprehensive Kinetic and Mechanistic Analysis of TiO₂ Photocatalytic Reactions According to the Direct–Indirect Model: (I) Theoretical Approach. *Journal of Physical Chemistry C* 2014;118(26):14266–14275.
- [11] Montoya J, Atitar FM, Bahnemann DW, Peral J, and, Salvador P. Comprehensive Kinetic and Mechanistic Analysis of TiO₂ Photocatalytic Reactions According to the Direct-Indirect (DI) Model: II) Experimental Validation. *Journal of Physical Chemistry C* 2014;118(28):14276–14290.
- [12] Miranda PB, Shen YR. Liquid Interfaces: A Study by Sum-Frequency Vibrational Spectroscopy. *Journal of Physical Chemistry B* 1999;103(17):3292–307.
- [13] Drevillon B. Spectroscopic Ellipsometry in the Infrared Range. *Thin Solid Films* 1998;313-314:625–630.
- [14] Michael JW, Shouzhong Z, Ho YHC. The New Interfacial Ubiquity of Surface-Enhanced Raman Spectroscopy *Analytical Chemistry* 2000; 72: 38–47.
- [15] McQuillan AJ. Probing Solid–Solution Interfacial Chemistry with ATR-IR Spectroscopy of Particle Films. *Advanced Materials* 2001;13(12-13):1034–1038.
- [16] Simonescu C. Advanced Aspects of Spectroscopy. Akhyar Farrukh M (ed.). InTech 2012. ISBN: 978-953-51-0715-6. Available from : <http://www.intechopen.com/books/advanced-aspects-of-spectroscopy>.
- [17] Tejedor MI, Anderson MA. In Situ Attenuated Total Reflection Fourier Transform Infrared Studies of the Goethite (α-FeOOH)-Aqueous Solution Interface. *Langmuir* 1986;2(2):203–210.
- [18] Hug S, Sulzberger B. In situ Fourier Transform Infrared Spectroscopic Evidence for the Formation of Several Different Surface Complexes of Oxalate on TiO₂ in the Aqueous Phase. *Langmuir* 1994;18(12):3587–3597.
- [19] Connor P, Dobson K, McQuillan AJ. New Sol-gel Attenuated Total Reflection Infrared Spectroscopic Method for Analysis of Adsorption at Metal Oxide Surfaces in Aqueous Solutions. Chelation of TiO₂, ZrO₂, and Al₂O₃ Surfaces by Catechol, 8-Quinolol, and Acetylacetone. *Langmuir* 1995;(6):4193–4195.
- [20] Roddick-Lanzilotta A, Connor P, McQuillan AJ. An In Situ Infrared Spectroscopic Study of the Adsorption of Lysine to TiO₂ from an Aqueous Solution. *Langmuir* 1998;(17):6479–6484.

- [21] Roddick-Lanzilotta A, McQuillan AJ. An In Situ Infrared Spectroscopic Investigation of Lysine Peptide and Polylysine Adsorption to TiO_2 from Aqueous Solutions. *Journal of Colloid and Interface Science* 1999;217(1):194–202.
- [22] Beaussart A, Petrone L, Mierczynska-Vasilev A, McQuillan AJ, Beattie DA. In Situ ATR FTIR Study of Dextrin Adsorption on Anatase TiO_2 . *Langmuir* 2012;28(9):4233–4240.
- [23] Mendive CB, Bredow T, Blesa MA, Bahnemann DW. ATR-FTIR Measurements and Quantum Chemical Calculations Concerning the Adsorption and Photoreaction of Oxalic Acid on TiO_2 . *Physical Chemistry Chemical Physics PCCP* 2006;8(27):3232–3247.
- [24] Mendive CB, Bredow T, Feldhoff A, Blesa MA, Bahnemann DW. Adsorption of Oxalate on Anatase (100) and Rutile (110) Surfaces in Aqueous Systems: Experimental Results vs. Theoretical Predictions. *Physical Chemistry Chemical Physics* 2009;11(11):1794–1808.
- [25] Stuart B. *Infrared Spectroscopy: Fundamentals and Applications*. Wiley 2004.
- [26] Hind AR, Bhargava SK, McKinnon A. At the Solid/Liquid Interface: FTIR/ATR — The Tool of Choice. *Advances in Colloid and Interface Science* 2001;93(1-3):91–114.
- [27] Smith BC. *Fundamentals of Fourier Transform Infrared Spectroscopy* (Second Edition). CRC Press Taylor & Francis Group 2011.
- [28] Harrick NJ. Surface Chemistry from Spectral Analysis of Totally Internally Reflected Radiation. *Journal of Physical Chemistry* 1960;64(9):1110–1114.
- [29] Fahrenfort J. Attenuated Total Reflection: A New Principle for the Production of Useful Infrared Reflection Spectra of Organic Compounds. *Spectrochimica Acta* 1961;17(7):698–709.
- [30] Mudunkotuwa IA, Al Minshid A, Grassian VH. ATR-FTIR Spectroscopy as a Tool to Probe Surface Adsorption on Nanoparticles at the Liquid-Solid Interface in Environmentally and Biologically Relevant Media. *Analyst* 2014;139(5):870–881.
- [31] Khoshhesab ZM. *Infrared Spectroscopy - Materials Science, Engineering and Technology*. Theophile T (ed). InTech 2012. ISBN:978-953-51-0537-4. Available from: <http://www.intechopen.com/books/infrared-spectroscopy-materials-science-engineering-and-technology/fundamental-of-reflectance-ir-spectroscopy>
- [32] Vigano C, Ruyschaert JM, Goormaghtigh E. Sensor Applications of Attenuated Total Reflection Infrared Spectroscopy. *Talanta* 2005;65(5):1132–1142.
- [33] Almeida AR, Moulijn JA, Mul G. In Situ ATR-FTIR Study on the Selective Photo-oxidation of Cyclohexane over Anatase TiO_2 . *Journal of Physical Chemistry C* 2008;112(5):1552–1561.

- [34] Bourikas K, Kordulis C, Lycourghiotis A. Titanium Dioxide (Anatase and Rutile): Surface Chemistry, Liquid-Solid Interface Chemistry, and Scientific Synthesis of Supported Catalysts. *Chemical Reviews* 2014;114:9754–9823.
- [35] Hodgson A, Haq S. Water Adsorption and the Wetting of Metal Surfaces. *Surface Science Reports* 2009;64(9):381–451.
- [36] Henderson M. The Interaction of Water with Solid Surfaces: Fundamental Aspects Revisited. *Surface Science Reports* 2002;46(1-8):1–308.
- [37] Mendive CB, Hansmann D, Bredow T, Bahnemann D. New Insights into the Mechanism of TiO₂ Photocatalysis: Thermal Processes beyond the Electron–Hole Creation. *Journal of Physical Chemistry C* 2011;115(40):19676–85.
- [38] Takeuchi M, Martra G, Coluccia S, Anpo M. Investigations of the Structure of H₂O Clusters Adsorbed on TiO₂ Surfaces by Near-Infrared Absorption Spectroscopy. *Journal of Physical Chemistry B* 2005;109(15):7387–7391.
- [39] Warren D, McQuillan AJ. Influence of Adsorbed Water on Phonon and UV-Induced IR Absorptions of TiO₂ Photocatalytic Particle Films. *Journal of Physical Chemistry B* 2004;19373–19379.
- [40] Almeida AR, Calatayud M, Tielens F, Moulijn JA, Mul G. Combined ATR-FTIR and DFT Study of Cyclohexanone Adsorption on Hydrated TiO₂ Anatase Surfaces. *Journal of Physical Chemistry C* 2011;115(29):14164–14172.
- [41] Li G, Li L, Boerio-Goates J, Woodfield BF. High Purity Anatase TiO₂ Nanocrystals: Near Room-Temperature Synthesis, Grain Growth Kinetics, and Surface Hydration Chemistry. *Journal of American Chemical Society* 2005;127(24):8659–8666.
- [42] Rubasinghege G, Grassian VH. Role(s) of Adsorbed Water in the Surface Chemistry of Environmental Interfaces. *Chemical Communications (Cambridge)* 2013;49(30):3071–3094.
- [43] Uosaki K, Yano T, Nihonyanagi S. Interfacial Water Structure at As-prepared and UV-induced Hydrophilic TiO₂ Surfaces Studied by Sum Frequency Generation Spectroscopy and Quartz Crystal Microbalance. *Journal of Physical Chemistry B* 2004;108(50):19086–19088.
- [44] Sakai N, Fujishima A, Watanabe T, Hashimoto K. Quantitative Evaluation of the Photoinduced Hydrophilic Conversion Properties of TiO₂ Thin Film Surfaces by the Reciprocal of Contact Angle. *Journal of Physical Chemistry B* 2003;107(4):1028–1035.
- [45] Young AG, McQuillan AJ. Adsorption/Desorption Kinetics from ATR-IR Spectroscopy. Aqueous Oxalic Acid on Anatase TiO₂. *Langmuir* 2009;25(6):3538–3548.
- [46] Dobson KD, McQuillan AJ. In Situ Infrared Spectroscopic Analysis of the Adsorption of Aliphatic Carboxylic Acids to TiO₂, ZrO₂, Al₂O₃, and Ta₂O₅ from Aqueous Solu-

- p>tions.
- Spectrochimica Acta Part A Molecular and Biomolecular Spectroscopy*
- 1999;55(7-8):1395–1405.
- [47] Begonja S, Rodenas L, Borghi EB, Morando PJ. Adsorption of Cysteine on TiO₂ at Different pH Values: Surface Complexes Characterization by FTIR-ATR and Langmuir Isotherms Analysis. *Colloids and Surfaces A: Physicochemical and Engineering Aspects* 2012;403:114–120.
  - [48] Gulley-Stahl H, Hogan PA, Schmidt WL, Wall SJ, Buhrlage A, Bullen HA. Surface Complexation of Catechol to Metal Oxides: An ATR-FTIR, Adsorption, and Dissolution Study. *Environmental Science and Technology* 2010;44(11):4116–4121.
  - [49] Popova G. In Situ FTIR Study of Pyridine-3-carbaldehyde Adsorption on TiO₂ (Anatase) and V-Ti-O Catalyst. *Reaction Kinetics and Catalysis Letters* 2004;83(2):353–360.
  - [50] Chernobay GB, Chesalov YA, Baltakhinov VP, Popova GY, Andrushkevich TV. In Situ FTIR Study of β -picoline Transformations on V–Ti–O Catalysts. *Catalysis Today* 2011;164(1):58–61.
  - [51] Chesalov YA, Chernobay GB, Andrushkevich TV. FTIR Study of the Surface Complexes of β -picoline, 3-pyridine-carbaldehyde and Nicotinic acid on Sulfated TiO₂ (Anatase). *Journal of Molecular Catalysis A: Chemical* 2013;373:96–107.
  - [52] Koczoń P, Dobrowolski JC, Lewandowski W, Mazurek AP. Experimental and Theoretical IR and Raman Spectra of Picolinic, Nicotinic and Isonicotinic Acids. *Journal of Molecular Structure* 2003;655(1):89–95.
  - [53] Nakamoto K. *Infrared and Raman Spectra of Inorganic and Coordination Compounds: Part B: Applications in Coordination, Organometallic, and Bioinorganic Chemistry*. 6th edition. Wiley 2008.
  - [54] Atitar MF, Dillert R, Bahnemann DW. An In Situ ATR-FTIR Study of the Adsorption of Imazapyr Herbicide onto TiO₂ Surface. Unpublished Results.
  - [55] Nanayakkara CE, Dillon JK, Grassian VH. Surface Adsorption and Photochemistry of Gas-Phase Formic Acid on TiO₂ Nanoparticles: The Role of Adsorbed Water in Surface Coordination, Adsorption Kinetics, and Rate of Photoproduct Formation. *Journal of Physical Chemistry C* 2014;118(44):25487–25495.
  - [56] Petrone L, McQuillan AJ. Alginate Ion Adsorption on a TiO₂ Particle Film and Interactions of Adsorbed Alginate with Calcium Ions Investigated by Attenuated Total Reflection Infrared (ATR-IR) Spectroscopy. *Applied Spectroscopy* 2011;65(10):1162–1169.
  - [57] Qu Q, Geng H, Peng R, Cui Q, Gu X, Li F, Wang M. Chemically Binding Carboxylic Acids onto TiO₂ Nanoparticles with Adjustable Coverage by Solvothermal Strategy. *Langmuir* 2010;26(12):9539–46.
  - [58] Hug SJ, Bahnemann DW. Infrared Spectra of Oxalate, Malonate and Succinate Adsorbed on the Aqueous Surface of Rutile, Anatase and Lepidocrocite Measured with In

- Situ ATR-FTIR. *Journal of Electron Spectroscopy and Related Phenomena* 2006;150(2-3):208–219.
- [59] Vittadini A, Selloni A, Rotzinger FP, Grätzel M. Formic Acid Adsorption on Dry and Hydrated TiO₂ Anatase (101) Surfaces by DFT Calculations. *Journal of Physical Chemistry B* 2000;104(101):1300–1306.
- [60] Mendive CB, Blesa MA, Bahnemann DW. The Adsorption and Photodegradation of Oxalic Acid at the TiO₂ Surface. *Water Science and Technology* 2005;55(12):139–145.
- [61] Mendive CB, Bredow T, Schneider J, Blesa M, Bahnemann DW. Oxalic Acid at the TiO₂/Water Interface under UV(A) Illumination: Surface Reaction Mechanisms. *Journal of Catalysis* 2015;322:60–72.
- [62] Mendive CB, Bahnemann DW, Blesa MA. Microscopic Characterization of the Photocatalytic Oxidation of Oxalic Acid Adsorbed onto TiO₂ by FTIR-ATR. *Catalysis Today* 2005;101(3-4):237–244.
- [63] Mendive CB, Bredow T, Feldhoff A, Blesa MA, Bahnemann DW. Adsorption of Oxalate on Rutile Particles in Aqueous Solutions: A Spectroscopic, Electron-Microscopic and Theoretical Study. *Physical Chemistry Chemical Physics PCCP* 2008;10:1960–1974.
- [64] Ojamäe L, Aulin C, Pedersen H, Käll P-O. IR and Quantum-Chemical Studies of Carboxylic Acid and Glycine Adsorption on Rutile TiO₂ Nanoparticles. *Journal of Colloid and Interface Science* 2006;296(1):71–78.
- [65] Rotzinger FP, Kesselman-Truttmann JM, Hug SJ, Shklover V, Grätzel M. Structure and Vibrational Spectrum of Formate and Acetate Adsorbed from Aqueous Solution onto the TiO₂ Rutile (110) Surface. *Journal of Physical Chemistry B* 2004;108(16):5004–5017.
- [66] Chen Y, Lin Y-F, Peng Z, Lin J. Transmission FT-IR Study on the Adsorption and Reactions of Lactic Acid and Poly(lactic Acid) on TiO₂. *Journal of Physical Chemistry C* 2010;114(41):17720–17727.
- [67] Kirwan LJ, Fawell PD, Van Bronswijk W. In Situ FTIR-ATR Examination of Poly(acrylic Acid) Adsorbed onto Hematite at Low pH. *Langmuir* 2003;19(14):5802–5807.
- [68] Martra G, Horikoshi S, Anpo M, Coluccia S, Hidaka H. FTIR Study of Adsorption and Photodegradation of L- α -alanine on TiO₂ Powder. *Research on Chemical Intermediates* 2002;28(4):359–371.
- [69] Dolamic I, Burgi T. In Situ ATR-IR Study on the Photocatalytic Decomposition of Amino Acids over Au/TiO₂ and TiO₂. *Journal of Physical Chemistry C* 2011;115(5):2228–2234.
- [70] Mitchell W, Goldberg S, Al-Abadleh HA. In Situ ATR-FTIR and Surface Complexation Modeling Studies on the Adsorption of Dimethylarsinic Acid and p-Arsanilic

- Acid on Iron-(oxyhydr)Oxides. *Journal of Colloid and Interface Science* 2011;358(2): 534–540.
- [71] Depalma S, Cowen S, Hoang T, Al-Abadleh HA. Adsorption Thermodynamics of p-Arsanilic Acid on Iron (Oxyhydr)Oxides: In-Situ ATR-FTIR Studies. *Environmental Science and Technology* 2008;42(6):1922–1927.
- [72] Roddick-Lanzilotta A, McQuillan AJ. An In Situ Infrared Spectroscopic Study of Glutamic Acid and of Aspartic Acid Adsorbed on TiO₂: Implications for the Biocompatibility of Titanium. *Journal of Colloid and Interface Science* 2000;227(1):48–54.
- [73] Guan X, Chen G, Shang C. ATR-FTIR and XPS Study on the Structure of Complexes Formed upon the Adsorption of Simple Organic Acids on Aluminum Hydroxide. *Journal of Environmental Science* 2007;19(4):438–443.
- [74] Peak D, Luther GW, Sparks DL. ATR-FTIR Spectroscopic Studies of Boric Acid Adsorption on Hydrous Ferric Oxide. *Geochimica et Cosmochimica Acta* 2003;67(14): 2551–2560.
- [75] Araujo PZ, Mendive CB, Rodenas LA. G, Morando PJ, Regazzoni AE, Blesa MA, Bahnemann DW. FT-IR-ATR as a Tool to Probe Photocatalytic Interfaces. *Colloids and Surfaces A: Physicochemical and Engineering Aspects* 2005;265(1-3):73–80.
- [76] Araña J, Pulido Melián E, Rodríguez López VM, Peña Alonso A, Doña Rodríguez JM, González Díaz O, Perez Pena J. Photocatalytic Degradation of Phenol and Phenolic Compounds Part I. Adsorption and FTIR Study. *Journal of Hazardous Materials* 2007;146(3):520–528.
- [77] Martin ST, Kesselman JM, Park DS, Lewis NS, Hoffmann MR. Surface Structures of 4-Chlorocatechol Adsorbed on Titanium Dioxide. *Environmental Science and Technology* 1996;30(8):2535–2542.
- [78] Mudunkotuwa IA, Grassian VH. Citric Acid Adsorption on TiO₂ Nanoparticles in Aqueous Suspensions at Acidic and Circumneutral pH: Surface Coverage, Surface Speciation, and Its Impact on Nanoparticle-Nanoparticle Interactions. *Journal of American Chemical Society*. 2010;132(42):14986–14994.
- [79] Hernández-Alonso MD, Almeida AR, Moulijn JA, Mul G. Identification of the Role of Surface Acidity in the Deactivation of TiO₂ in the Selective Photo-Oxidation of Cyclohexane. *Catalysis Today* 2009;143(3-4):326–333.
- [80] Almeida A, Moulijn J, Mul G. Photocatalytic Oxidation of Cyclohexane over TiO₂: Evidence for a Mars–Van Krevelen Mechanism. *Journal of Physical Chemistry C* 2011;1330–1338.
- [81] Borer P, Hug SJ. Photo-Redox Reactions of Dicarboxylates and α -Hydroxydicarboxylates at the Surface of Fe(III)(hydr)Oxides Followed with in Situ ATR-FTIR Spectroscopy. *Journal of Colloid and Interface Science* 2014;416:44–53.

- [82] Bahri S, Jonsson CM, Jonsson CL, Azzolini D, Sverjensky DA, Hazen RM. Adsorption and Surface Complexation Study of L-DOPA on Rutile (α -TiO₂) in NaCl Solutions. *Environmental Science and Technology* 2011;45(9):3959–3966.
- [83] Nadtochenko VA, Rincon AG, Stanca SE, Kiwi J. Dynamics of E.coli Membrane Cell Peroxidation During TiO₂ Photocatalysis Studied by ATR-FTIR Spectroscopy and AFM Microscopy. *Journal of Photochemical and Photobiological Science A Chemistry* 2005;169(2):131–137.
- [84] Tan J, Yang L, Kang Q, Cai Q. In Situ ATR-FTIR and UV-Visible Spectroscopy Study of Photocatalytic Oxidation of Ethanol over TiO₂ Nanotubes. *Analytical Letters* 2011;44(6):1114–1125.
- [85] Hwang YS, Lenhart JJ. Adsorption of C4-dicarboxylic Acids at the Hematite/Water Interface. *Langmuir* 2008;24(24):13934–13943.
- [86] Araujo PZ, Morando PJ, Martínez E, Blesa MA. Time Evolution of Surface Speciation During Heterogeneous Photocatalysis: Gallic Acid on Titanium Dioxide. *Applied Catalysis B Environmental* 2012;125:215–221.
- [87] Ekström GN, McQuillan AJ. In Situ Infrared Spectroscopy of Glyoxylic Acid Adsorption and Photocatalysis on TiO₂ in Aqueous Solution. *Journal of Physical Chemistry B* 1999;103(48):10562–10565.
- [88] Hirakawa T, Sato K, Komano A, Kishi S, Nishimoto CK, Mera N, Kugishima M, Sano T, Ichinose H, Negishi N, Seto Y, Takeuchi K. Experimental Study on Adsorption and Photocatalytic Decomposition of Isopropyl Methylphosphonofluoridate at Surface of TiO₂ Photocatalyst. *Journal of Physical Chemistry C* 2010;114(5):2305–2314.
- [89] Hu X, Burgi T. Photoinduced Electron Transfer and Photodegradation of Malonic Acid at Au/TiO₂ Investigated by In Situ ATR-IR Spectroscopy. *Applied Catalysis A General* 2012;449:139–144.
- [90] Dolamic I, Burgi T. Photocatalysis of Dicarboxylic Acids over TiO₂: An In Situ ATR-IR Study. *Journal of Catalysis* 2007;248(2):268–276.
- [91] Baltrusaitis J, Schuttlefield J, Jensen JH, Grassian VH. FTIR Spectroscopy Combined with Quantum Chemical Calculations to Investigate Adsorbed Nitrate on Aluminum Oxide Surfaces in the Presence and Absence of Co-adsorbed Water. *Physical Chemistry Chemical Physics PCCP* 2007;9(36):4970–4980.
- [92] Hwang YS, Liu J, Lenhart JJ, Hadad CM. Surface Complexes of Phthalic Acid at the Hematite/Water Interface. *Journal of Colloid and Interface Science* 2007;307(1):124–134.
- [93] Araña J, Tello Rendón E, Doña Rodríguez JM, Herrera Melián JA, González Díaz O, Pérez Peña J. High Concentrated Phenol and 1,2-propylene Glycol Water Solutions Treatment by Photocatalysis. *Applied Catalysis B Environmental* 2001;30(1-2):1–10.

- [94] Kesselman-Truttmann JM, Hug SJ. Photodegradation of 4,4'-Bis(2-sulfostyryl)biphenyl (DSBP) on Metal Oxides Followed by In Situ ATR-FTIR Spectroscopy. *Environmental Science and Technology* 1999;33(18):3171–3176.
- [95] Bronswijk W Van, Kirwan LJ, Fawell PD. In Situ Adsorption Densities of Polyacrylates on Hematite Nano-particle Films as Determined by ATR-FTIR Spectroscopy. *Vibrational Spectroscopy* 2006;41(2):176–181.
- [96] Green IX, Buda C, Zhang Z, Neurock M, Yates JT. IR Spectroscopic Measurement of Diffusion Kinetics of Chemisorbed Pyridine through TiO₂ Particles. *Journal of Physical Chemistry C* 2010;114(39):16649–16659.
- [97] Popova GY, Chesalov YA, Andrushkevich TV. In situ FTIR Study of Pyridine-3-carbaldehyde Adsorption on TiO₂ (Anatase) and V-Ti-O Catalyst. *Reaction Kinetics and Catalysis Letters*. 2004;83(2):353–360.
- [98] Pe C, Kador L, Peng B, Thelakkat M. Characterization of the Adsorption of Ru-bpy Dyes on Mesoporous TiO₂ Films with UV - Vis, Raman, and FTIR Spectroscopies. *Journal of Physical Chemistry B* 2006;110(17):8723–8730.
- [99] Maira A, Coronado J, Augugliaro V, Yeung K, Conesa J, Soria J. Fourier Transform Infrared Study of the Performance of Nanostructured TiO₂ Particles for the Photocatalytic Oxidation of Gaseous Toluene. *Journal of Catalysis* 2001;202(2):413–420.
- [100] Lin H, Long J, Gu Q, Zhang W, Ruan R, Li Z, Wang X. In Situ IR Study of Surface Hydroxyl Species of Dehydrated TiO₂: Towards Understanding Pivotal Surface Processes of TiO₂ Photocatalytic Oxidation of Toluene. *Physical Chemistry Chemical Physics* 2012;14(26):9468–9474.